

NAS633 (UNS S35000)

High Strength Stainless Steel

NAS633 is a semi-austenitic precipitation-hardening stainless steel. It has excellent workability after solution heat treatment and also offers good weldability. High strength can be achieved through heat treatment.

Steel Grade/Standard

Nippon Yakin Grade	ASTM A693
NAS633	UNS S35000

Chemical Composition

	C	Si	Mn	P	S	Ni	Cr	Mo
Specification (ASTM A693 TYPE633)	0.07 ~0.11	≤0.50	0.50~1.25	≤0.040	≤0.030	4.0~5.0	16.0~17.0	2.5~3.2

Mechanical Properties and Hardness

Table 1: Mechanical properties ASTM A693

Thickness (mm)	Heat Treatment	Finish	Proof stress (N/mm ²)	Tensile strength (N/mm ²)	Elongation (%)	Hardness (HV)
0.05~0.13 excl	Solution	BA	≤595	≤1380	≥8	≤302
0.13~0.25 excl	Solution	BA	≤585	≤1380	≥8	≤302
Over 0.254	Solution	BA	≤585	≤1380	≥12	≤302
Example 0.254	Solution	BA	481	1230	23	256

Table 2 Example of mechanical properties after SCT

Treatment	Processing conditions	Thickness (mm)	Proof stress (N/mm ²)	Tensile strength (N/mm ²)	Elongation (%)	Hardness (HV)
Ageing SCT850	930°Cx10min ⇒ -73°Cx3hr ⇒ 455°Cx3hr	0.254	1413	1605	8	465

Production capability

Finish : BA
Thickness : 0.05mm ~ 0.5mm
Width : 5mm ~ 510mm

Application

Welded bellows, Formed bellows



For more information, please contact:
NAS Stainless Steel Strip MFG. Co., Ltd.
(NAS KOTAI)
Marketing & Development Dept.
Overseas Sales Dept.
Tel: +81-3-5205-2541

Notes regarding the handling of property data ; The technical information in this product guide is representative values obtained in property test and other items used to explain the performance of the product. With the exception of specifically mentioned as provisions of a "Standards", the contents do not represent guaranteed upper limit or lower limit values. The respective data given on this paper are typical examples and may be different in some cases from actual products. No responsibility shall, therefore, be assumed for damages arising from using this paper. This information is also subject to change in the future without notice.