

NASPB

Soft Magnetic Material

NASPB is a soft magnetic Fe-Ni alloy with about 48%Ni. It is a high magnetic permeability alloy with comparatively high saturation magnetic flux density. Nippon Yakin supplies NASPB in sheet and strip forms.

Chemical Composition

	C	Si	Mn	Ni	Fe
Specification (NASPB)	≤0.05	≤0.05	≤0.80	45.0~49.0	Bal.

[wt %]

Physical Properties

Density	[g/cm ³]	8.2
Specific heat	[J/kg · K]	450
Electrical resistivity	[μΩ · cm]	44
Average coefficient of thermal expansion	[10 ⁻⁶ /°C] 25~100°C	9
Curie point	[°C]	460
Magnetism		Ferromagnetic
Melting range	[°C]	1416~1444




NIPPON YAKIN KOGYO CO., LTD.

Mechanical Properties


Mechanical Properties at Room Temperature

	0.2% proof stress [MPa]	Tensile strength [MPa]	Elongation [%]	Hardness [HV]
Cold rolled and annealed material	260	520	35	140

Work Hardening Properties



Softening Properties



Magnetic Properties


DC Magnetic Properties

Sheet thickness [mm]	Initial relative permeability [μ_i]	Maximum relative permeability [μ_m]	Coercivity [A/m]	Saturation magnetic flux density [T]	Magnetic annealing conditions
0.35	11,000	130,000	3.5	1.5	1100°C×3hr
0.35	19,000	175,000	2.9	1.5	1180°C×4hr

AC Magnetic Properties

Sheet thickness [mm]	Magnetic annealing conditions	Effective permeability [μ_e]	
		300Hz	1kHz
0.35	1100°C×3hr	4,000	2,000
0.35	1180°C×4hr	3,800	1,800

Effect of Magnetic Annealing Conditions on Magnetic Properties



Applications

Current/voltage sensors, Electronic components, Magnetic shields.

For more information, please contact:

Nippon Yakin Kogyo Co., Ltd.

Material Solutions Sales Department

San-Ei Bldg., 5-8, 1-chome Kyobashi, Chuo-ku,
Tokyo 104-8365 Japan

TEL: +81-3-3273-4649 FAX: +81-3-3273-4642

URL: <https://www.nyk.co.jp/en/>

Note regarding the handling of property data:

The technical information contained in this product guide is representative values obtained in property tests and other items used to explain the performance of the product. With the exception of items specifically mentioned as provisions of a "Standard," the contents do not represent guaranteed upper limit or lower limit values. The respective data given on this technical information are typical examples and may be different in some cases from the data obtained from the actual product. No responsibility shall, therefore, be assumed for damages arising from using the technical information data. This information is also subject to change in the future without notice. To obtain the most recent information, please contact Nippon Yakin. No part of this document may be copied or reproduced in any form without the consent of Nippon Yakin.